

Surfacing Selection Guide

| Existing Surface | Slope | Solvent or Water Based | Base Coat | # of Plys | New Surfacing | Guide Spec # |
|-------------------------------------|--------------------|------------------------|----------------------|-------------|---|----------------|
| Smooth BUR, APP, SBS or Granule Cap | Dead level to 1/2" | SB | RX-200 4-5 gal/sq | — | Granules 60 lbs/sq | RX-BU-200-CG |
| Smooth BUR, APP, SBS or Granule Cap | Dead level to 1/2" | SB | RX-200 6 gal/sq | 1 polyester | Granules 60 lbs/sq | RX1-BU-200-CG |
| Smooth BUR, APP, SBS or Granule Cap | 1/4" to vertical | SB | RX-200 6 gal/sq | 1 polyester | RX-460 .75-1.25 gal/sq | RX1-BU-200-460 |
| Smooth BUR, APP, SBS or Granule Cap | 1/4" to vertical | WB/SB | RX-300 2 gal/sq | — | RX-450 1-1.5 gal/sq | RX-BU-300 |
| Smooth BUR, APP, SBS or Granule Cap | 1/4" to vertical | WB | RX-300 4 gal/sq | 1 polyester | RX-700 3 gal/sq (2 coats) | RX1-BU-300-AC |
| Smooth BUR, APP, SBS or Granule Cap | 1/4" to vertical | WB | RX-300 8 gal/sq | 2 polyester | RX-700 3 gal/sq (2 coats) | RX2-BU-300-AC |
| Smooth BUR, APP, SBS or Granule Cap | 1/4" to vertical | WB | — | — | RX-500 3 gal/sq (2 coats) | RX-BU-500 |
| Smooth BUR, APP, SBS or Granule Cap | 1/4" to vertical | WB | — | — | RX-700 3 gal/sq (2 coats) | RX-BU-700 |
| Smooth BUR, APP, SBS or Granule Cap | 1/4" to vertical | WB | RX-700 3 gal/sq | 1 polyester | RX-700 4 gal/sq (2 coats) | RX1-BU-PA-700 |
| Smooth BUR, APP, SBS or Granule Cap | 1/4" to vertical | SB | — | — | RX-450 1-1.5 gal/sq | RX-BU-450 |
| Smooth BUR, APP, SBS or Granule Cap | 1/4" to vertical | SB | — | — | RX-460 0.75-1.25 gal/sq | RX-BU-460 |
| Gravel | Dead level to 1/2" | SB | RX-200 10 gal/sq | — | Gravel 400 lbs/sq | RX-GR-200-GR |
| Metal | 1 to vertical | WB | — | — | RX-500 3 gal/sq (2 coats) | RX-ME-500 |
| Metal | 1 to vertical | WB | — | — | RX-700 3 gal/sq (2 coats) | RX-ME-700 |
| Metal | 1 to vertical | SB | — | — | RX-900 2 gal/sq (2 coats) | RX-ME-900 |
| Single Ply | 1/4" to vertical | SB | — | — | RX-900 2.5 gal/sq [0.5 gal: 1st coat 1 gal: 2nd coat 1 gal: 3rd coat] | RX-SP-900 |